

No Mix Activator

Mix ratios by weight for No Mix HS & MS

- The use of LV-418 is mandatory for formulas containing LV-29 and for Lifetime Warranty of No Mix HS. It is optional for all other HS & MS formulations but highly recommended to improve chip resistance and flexibility especially when applying tri-coats.
- Activate only what you intend to spray, the pot life of activated No Mix HS & MS is 8 hours. While the color may not gel after 8 hours, it may become seedy.
- Mixing by Volume: Add ½ fl. oz. of LV-418 to 1 ready to use quart of No Mix HS or MS.
- Mixing by Weight: Use the chart below.

| Amount RTU HS or MS | LV-418 grams |
|---------------------|--------------|
| ¼ pint (4 oz) | 2.3g |
| ½ pint (8 oz) | 4.6g |
| 1 pint (16 oz) | 9.2g |
| 1 quart (32 oz) | 18.3g |
| 2 quarts (64 oz) | 36.6g |
| 3 quarts (96 oz) | 54.0g |
| 1 gallon (128 oz) | 73.3g |